


Cu-alloy Coated Silica Fibers

art photonics' Copper-alloy Coated Silica Fibers are the optimal solution for applications in high temperature, vacuum and harsh environment conditions. Cu-alloy coated fibers have all benefits of silica-silica fibers. Additional significant advantages include a superior mechanical strength and better fatigue resistance compared to polymer coated fibers.

The transmission range spans 220 to 2400 nm depending on UV or NIR silica fiber core choice. The working temperature range is from -270°C to 600°C; humidity – up to 100%.



Applications:

- ✓ High temperature environments
- ✓ Harsh Chemical environments
- ✓ Nuclear radiation resistant devices
- ✓ Down-hole sensing for oil and gas industry
- ✓ High Power Laser delivery
- ✓ Medical applications
- ✓ Soldered fiber bundles


Features:

- ✓ Working temperature up to 600°C
- ✓ Excellent mechanical strength and flexibility
- ✓ No outgassing under high vacuum conditions
- ✓ Solderable into connectors (epoxy-free option)
- ✓ Effective heat rejection along metal coating
- ✓ Steaming, ETO, e-beam or gamma sterilizable

Parameters of standard Cu-alloy coated fibers

Code	Type	Core, μm	Cladding, μm	Coating Cu, μm	NA
100/110 Cu	Step Index Multimode	$100 \pm 2\%$	$110 \pm 2\%$	$145 \pm 5\%$	0.22
200/220 Cu	Step Index Multimode	$200 \pm 2\%$	$220 \pm 2\%$	$270 \pm 5\%$	0.22
400/440 Cu	Step Index Multimode	$400 \pm 2\%$	$440 \pm 2\%$	$535 \pm 5\%$	0.22
600/660 Cu	Step Index Multimode	$600 \pm 2\%$	$660 \pm 2\%$	$745 \pm 5\%$	0.22
50/125 Cu	Graded Index Multimode	$50 \pm 2\%$	$125 \pm 2\%$	$165 \pm 2\%$	0.22
9/125 Cu	Graded Index Multimode	$9 \pm 5\%$	$125 \pm 2\%$	$165 \pm 2\%$	0.13

Attenuation for UV (High OH) and NIR (Low OH) Multimode Fiber



Specifications

Core/ Cladding material Step Index	Pure Fused Silica Core / Fluorine Doped Silica Cladding
Graded Index	Germanium Doped Fused Silica Core / Pure Fused Silica
Fiber core diameters, µm	9; 50; 62.5; 100; 200; 400; 600
Cu-alloy coating thickness, µm	15 - 50 (depending on fiber diameter)
Standard Numerical Aperture (NA)	0.22 ± 0.02
Available Numerical Aperture (NA)	0.12 ± 0.02 0.26 ± 0.02
Min operating temperature	-270°C
Max operating temperature	+600°C
Humidity Range	Up to 100%
Minimal bending radius (long term)	200 x fiber outer diameter
Minimal bending radius (short term)	100 x fiber outer diameter
Tensile strength (short gauge), GPa	3.5 - 6
Two point bending strength, GPa	> 10
Static fatigue parameter	> 100