

LIDT TEST RESULTS

LIDT VALUE

10^6 -on-1

$0.306^{+0.037}_{-0.037}$ J/cm²

CHARACTERISTIC DAMAGE CURVE

Table 1: Estimated LIDTs from fitting model for sample HL_F5_S1.

Test mode	Threshold (Catastrophic)	Threshold (Color mode)
1-on-1	$>0.476^{+0.051}_{-0.051}$ J/cm ²	-
10-on-1	$>0.476^{+0.051}_{-0.051}$ J/cm ²	-
10^2 -on-1	$0.380^{+0.042}_{-0.042}$ J/cm ²	-
10^3 -on-1	$0.380^{+0.042}_{-0.042}$ J/cm ²	-
10^4 -on-1	$0.339^{+0.037}_{-0.037}$ J/cm ²	-
10^5 -on-1	$0.339^{+0.037}_{-0.037}$ J/cm ²	$0.391^{+0.055}_{-0.053}$ J/cm ²
10^6 -on-1	$0.339^{+0.037}_{-0.037}$ J/cm ²	$0.306^{+0.037}_{-0.037}$ J/cm ²




Figure 2. Characteristic damage curve.